

WATERPROOFNESS TEST-HH	CHANGE OF DIMENSION		CHANGE OF APPEARANCE		
	THICKNESS-decor paper(mm)	THICKNESS-wearlayer(mm)	delamination	swell	other change
0h-Average:	0.06978	0.4216			
24h-Average:	0.06924	0.4309	NO	NO	NO
<b>different from 0h</b>	<b>-0.00054</b>	<b>0.0093</b>			
72h-Average:	0.06872	0.4102	NO	NO	NO
<b>different from 0h</b>	<b>-0.00106</b>	<b>-0.0114</b>			
144h-Average:	0.07026	0.4085	NO	NO	NO
<b>different from 0h</b>	<b>0.00048</b>	<b>-0.0131</b>			
216h-Average:	0.06881	0.4114	NO	NO	NO
<b>different from 0h</b>	<b>-0.00097</b>	<b>-0.0102</b>			
288h-Average:	0.06978	0.4051	NO	NO	NO
<b>different from 0h</b>	<b>0.00000</b>	<b>-0.0165</b>			
408h-Average:	0.06965	0.3999	NO	NO	NO
<b>different from 0h</b>	<b>-0.00013</b>	<b>-0.0217</b>			
488h-Average:	0.06978	0.4067	NO	NO	NO
<b>different from 0h</b>	<b>0.0000</b>	<b>-0.0149</b>			

